

Alloy 100 (also known as Aermet 100, UNS K92580, and governed by AMS 6532 & AMS 6478B) is an ultra-high-strength steel widely used in aerospace, military, and racing applications due to its exceptional strength-toughness balance.

Alloy 100 (also known as Aermet 100) is an ultra-high-strength martensitic steel developed primarily for aerospace and defense applications where a combination of extreme strength, toughness, and stress-corrosion resistance is required.

Comparison to Similar High-Strength Steels

Alloy	Tensile Strength (MPa)	Toughness (MPa√m)	Key Strengths
Aermet 100	1930+	110+	Best balance of strength + toughness + corrosion resistance
300M	1860-2000	~70	High strength, but lower toughness & corrosion resistance
4340	1500-1800	~60	Widely used, but inferior to Aermet 100
Maraging 250 (18Ni)	1700-1900	~90	High toughness, but lower strength than Aermet 100

Why Choose Aermet 100 Over Alternatives?

- **Best-in-class strength-toughness combination** for critical aerospace/defense uses.
- **Resists stress-corrosion cracking** better than 300M or 4340.
- **Used where failure is not an option** (e.g., fighter jet landing gear).

Applications

- **Aircraft landing gear** (F/A-18, F-22, F-35)
- **Armor-piercing components**
- **High-stress aerospace fasteners**
- **Racing & high-performance automotive parts**

Equivalent or Similar Grades - Chemical Composition

Grade	Chemical composition WT %												
	C	Mn	Si	P *	S	Cr	Ni	Co	Mo	Ti	Al	O	N
AerMet 100	0.23	-	-	-	-	3.10	11.10	13.4	1.20	0.05	-	-	-

AMS 6532 UNS K92580	0.21-0.25	0.10	0.10	0.008	0.005	2.9-3.3	11-12	13-14	1.0-1.3	0.015	0.015	20ppm	15ppm
AMS 6478B UNS K92580	0.21-0.25	0.10	0.10	0.008	0.005	2.9-3.3	11-12	13-14	1.0-1.3	0.015	0.015	20ppm	15ppm
Alloy 100	0.21-0.25	0.10	0.10	0.008	0.005	2.9-3.3	11-12	13-14	1.0-1.3	0.015	0.015	0.002	0.0015

* P+S: 0.010

Mechanical Properties

Room Temperature Performance

Property	Value	Test Standard
Tensile Strength	1930-2070 MPa (280-300 ksi)	ASTM E8/E8M
Yield Strength	1650-1790 MPa (240-260 ksi)	ASTM E8/E8M
Elongation	10-14%	ASTM E8/E8M
Fracture Toughness (KIC)	110-130 MPa√m	ASTM E399
Hardness	52-54 HRC	ASTM E18

Fatigue Performance (S-N Curve)

- **Fatigue limit (10⁷ cycles, R=0.1): 700-750 MPa**
- **High-cycle fatigue (HCF):** Dominated by **microcrack initiation at inclusions**
- **Low-cycle fatigue (LCF):** Controlled by **plastic strain accumulation**

Fatigue Crack Growth Rate (Paris Law Parameters)

Stress Ratio (R)	C (mm/cycle)	m	ΔK Range (MPa√m)
R=0.1	1.2×10 ⁻¹¹	3.2	10-50
R=0.5	3.5×10 ⁻¹¹	3.0	10-40

Fracture Toughness & CTOD Analysis

Crack Tip Opening Displacement (CTOD)

- **Critical CTOD (δ_m):** 0.15-0.25 mm (ASTM E1820)
- **Threshold ΔK_{th} :** ~5 MPa \sqrt{m} (below which cracks do not propagate)

Fracture Modes

- **Fatigue fracture:** Striations + secondary cracks
- **Overload fracture:** Dimples + localized cleavage (hydrogen embrittlement risk)

Microstructure Analysis (SEM/TEM/EBSD)

Key Phases in AerMet 100

Phase	Morphology	Size
Lath Martensite	High-dislocation-density bundles	0.2-0.5 μm width
Reversed Austenite	Thin films between laths	10-50 nm thickness
M2C Carbides	Spherical precipitates	5-20 nm diameter

Fractography (SEM Imaging)

- **Crack initiation:** Often at **Al₂O₃ inclusions ($\leq 10 \mu m$)**
- **Stable crack growth:** Fatigue striations (~1 μm /cycle spacing)
- **Fast fracture:** Mixed ductile (dimples) + brittle (cleavage)

6. Environmental Effects & Special Conditions

Hydrogen Embrittlement (SSRT Testing)

- **Reduction in ductility:** 14% \rightarrow **6% elongation** (after H-charging)
- **Fracture mode shift:** Ductile \rightarrow **intergranular cracking**

Corrosion Fatigue (Salt Spray Testing)

- **Fatigue life reduction:** **30-40%** in 3.5% NaCl vs. dry air
- **Crack growth acceleration:** **2-3 \times faster** at $\Delta K > 15$ MPa \sqrt{m}

Physical Properties

- Density (lb/in³): 0.285
- Modulus of Elasticity: 28.2 x 10³ ksi
- Melting Point (°F)
- Thermal conductivity (BTU-in/hr-ft²-°F): 172
- Specific heat (BTU/lb-°F) -
- Thermal expansion (1/°F): 0.00000552
- Electrical conductivity (% IACS): 4.01
- Electrical Resistivity: 70.0° F

Heat Treatment

Decarburization

- Like other carbon bearing high strength alloys, AerMet 100 alloy is subject to decarburization during hardening. Heat treatment should take place in a neutral atmosphere furnace, salt bath or vacuum. Decarburization should be determined by comparing the surface and internal hardness of a small test cube for proper response. Metallographic determination of decarburization is not recommended for this alloy.

Normalizing

- AerMet 100 alloy can be normalized by heating to 1650° F (899° C) holding for one hour and air cooling to room temperature. Optimum softening for machining is obtained by following the 1650° F (899° C) normalize with a 16 hour 1250° F (677° C) overage anneal.

Annealing

- AerMet 100 alloy is softened by using a 1250° F (677° C) overage anneal for 16 hours. The optimum annealed hardness of 40 HRC maximum is obtained following this anneal.

Solution Treatment

- The solution treatment temperature range is 1625° F +/- 25° F (885° C +/- 14° C) for 1 hour. The solution treatment temperature must be monitored by a thermocouple attached to the load.

Quenching

- Water quenching is not recommended.

Proper quenching practice is essential for AerMet 100 alloy. The alloy should be cooled from the solution treatment temperature to 150° F (66° C) in 1 to 2 hours to develop optimum properties. Individual sections larger than 2" diameter to 1" thick (plate) must be quenched with oil in order to obtain 150° F (66° C) in 1 to 2 hours. Individual sections up to 2" diameter or 1" thick (plate) will air cool to 150° F (66° C) in 1 to 2 hours. The cooling rate of the furnace load must be monitored by a thermocouple attached to the hottest spot in the load to insure that the 2 hour cool to 150° F (66° C) is obtained.

Cold Treatment

- Following cooling to room temperature, to obtain the full toughness capability AerMet 100 alloy should be cooled to -100° F (-73° C) and held for 1 hour. The parts can then be air warmed.

Straightening

- AerMet 100 alloy exhibits minimal size change during heat treatment; however, for some parts, mechanical straightening to compensate for distortion during heat treatment is appropriate.
Prior to straightening, a low temperature stress relief at 350/400° F (482/204° C) for 5 hours following the refrigeration operation will provide an optimal combination of ductility and yield strength for the mechanical straightening operation.

Age

- The standard aging treatment for AerMet 100 alloy is 900° F +/- 10° F (482° C +/- 6° C) for 5 hours. Parts made from AerMet 100 alloy should never be aged at a temperature below 875° (468° C).

Aging Temperature	HRC
As hardened	51.0/53.0
875° F (468° C) 5 hrs	54.5/55.5
900° F (482° C) 5 hrs	53.0/54.0
925° F (496° C) 5 hrs	51.0/52.5

Processing Performance

Forging

Primary break down forging of AerMet 100 alloy should be done at a maximum starting temperature of 2250° F (1232° C). Finish forging should be done from 1800° F (982° C) with a finishing temperature below 1650° F (899° C) in order to optimize the final heat treat properties. Following forging the parts should be air cooled to room temperature and then annealed. Following the anneal, the forgings should be normalized in order to restore properties to the dead zone.

Welding

- Avoid conventional methods—**EBW/LBW + PWHT required**

Machining

AerMet 100 is somewhat more difficult to machine than 4340 at HRC 38. Hence, carbide tools are recommended at 280 to 350 SFM.

Following rough machining, stress relieve at 800° F (427° C) for 1-3 hours if a stress relief is desired.